



## AQUALINE™ 1100

|                          |           |                       |
|--------------------------|-----------|-----------------------|
| <b>Base fabric</b>       |           | Polyester             |
| <b>Yarn</b>              |           | 1100 Denier           |
| <b>Construction</b>      |           | 12 x 12 cm            |
| <b>Coating</b>           |           | PVC/PU blend          |
| <b>Total weight</b>      |           | 1100 g/m <sup>2</sup> |
| <b>Tensile strength</b>  | DIN 53354 | 4110/3755 N/50mm      |
| <b>Tear strength</b>     | DIN 53363 | 415/375 N             |
| <b>Adhesion Strength</b> | DIN 53357 | 120 N/5cm             |
| <b>Surface Treatment</b> |           | 1 side Matt Lacquered |
| <b>Temperature range</b> | DIN 53361 | -30°C/70°C            |

Revision date: 06.12.2016/ Authorised by: GH

Data note: This data is based on average test results and supersedes any previous data. Dye stuffs used for various fibres and polymers have a tendency to migrate. We cannot guarantee that colour transfer will not occur if shades are mixed. Colour selection may change due to market requirements. Data shown is not legally binding.